

GeoKrete®-Water

TYPICAL PERFORMANCE CHARACTERISTICS*

- **Compressive Strength (ASTM C39 & C109)**
28-days $\geq$ 8,000 psi | 55.1 MPa
- **Flexural Strength (ASTM C78)**
28-days $\geq$ 800 psi | 5.5 MPa
- **Bond Strength (ASTM C882)**
28-days $\geq$ 3,000 psi | 20.7 MPa
- **Modulus of Elasticity (ASTM C469)**
28-days $\geq$ 5,490 ksi | 37.8 GPa
- **Chemical Resistance (ASTM C267)**
0% mass loss in 12 week
sulfuric acid @ pH 1.0 immersion
- **Chloride Ion Penetration Resistance (ASTM C1202)**
28-Day $\leq$ 250 Coulombs (very low)
- **Split Tensile Strength (ASTM C496)**
28-days $\geq$ 900 psi | 6.2 MPa
- **Shrinkage (ASTM C1090)**
28-days $\leq$ 0.02%
- **Freeze Thaw (ASTM C666)**
No visible damage after 300 cycles
- **Abrasion Resistance (ASTM C1138)**
6 Cycles at 28 Day – loss $\leq$ 1.0%

* The values stated in inch-pound units are to be regarded as the standard. The values given in International System are for information only.

Fully Structural and Corrosion Resistant Geopolymer Mortar for Potable Water Applications

DESCRIPTION

GeoKrete®-Water is a NSF 61 certified geopolymer liner material formulated to rehabilitate existing infrastructure, especially in moderately corrosive/abrasive environments (such as Ozone) restoring structural integrity and renewing the installations service life. GeoKrete-Water is a factory blended, one-component (just add water), eco-friendly, micro-fiber reinforced geopolymer mortar synthesized from reactive SiO_2 and Al_2O_3 from industrial byproducts, enhanced with monocryalline quartz aggregate. The GeoKrete-Water geopolymer reaction mechanism is alkali-activated polycondensation which yields superior physical properties and chemical resistance. It can be applied in one pass up to several inches thick on horizontal or vertical surfaces by low pressure spraying or spin cast application process.

RECOMMENDED FOR

Structural restoration of large diameter pipes, culverts and tunnels, including potable, raw, storm and wastewater, consisting of metal, concrete, stone, masonry and others. Other structures such as manholes, wet-wells, and treatment plant structures also benefit from the superior strength and corrosion resistance properties of this advanced, NSF certified geopolymer material.

FEATURES AND BENEFITS

- To be used in pipes 30 inches or greater in diameter, and tanks 1,000 gallons or greater.
- Quality controlled, one-component blend for uniform results.
- High early and ultimate compressive, flexural and bond strengths.
- Resistant to exposure to chemicals commonly used in water treatment at an occasional pH of 1.0 and temperatures up to 212°F | 100°C (steam).
- Extremely low permeability



Meets the Requirements of NSF/ANSI/CAN 61
Certified to NSF/ANSI/CAN 61



Certified to NSF/ANSI 61



REPAIR MATERIALS





WARRANTY

Quadex, LLC warrants its products to be free of defects in material and workmanship. Unless superseded by project specifications and terms agreed upon in writing between installer and Quadex prior to bid, if within one year from purchase, any Quadex, LLC product is proven defective, the company will replace said product or refund its purchase price at its sole discretion. The company's obligation shall be limited solely to such replacement or refund. There are no other warranties by Quadex, LLC, expressed or implied. There is no warranty if Quadex products are used contrary to Quadex, LLC's written directions.

PROCEDURE

Prepare surface to be patched by removing unsound concrete, dirt, dust, oil and other debris using high pressure (3,500 PSI | 241.3 bar) water blasting. Stop active infiltration. Then rinse with potable water to remove all remaining dirt, sand and loose debris. This will provide a clean, damp surface to allow for a good bond.

Use approximately 0.49 to 0.59 gallons | 1.85 to 2.23 liters of potable water per 60 lb. | 27.2 kg bag of GeoKrete geopolymer. For 1,000 lb. | 454 kg. supersack use approximately 8.0 to 9.5 gallons | 30.3 to 36 liters of potable water. First add water to mixer, start the mixer and add GeoKrete®-Water until mortar is completely mixed. Once all geopolymer material and water has been added to mixer, it needs to mix for approximately five (5) minutes prior to being transferred into the material hopper. Once fully mixed, additional water may be added, as approved by Quadex, should it be necessary for proper consistency.

Apply GeoKrete-Water geopolymer by low pressure spraying or the spin cast application process on horizontal or vertical surfaces to a monolithic minimum thickness of 1/2-inch | 12.7 mm for a protective layer to new infrastructure and 1.0-inch | 25.4 mm for structural restoration of or protective layer to existing infrastructure.

PACKAGING

GeoKrete-Water is supplied in 60 lb. | 27.2 kg. poly-lined bags or 1,000 lb. | 454 kg. super sacks.

YIELD

One 60 lb. | 27.2 kg. bag of GeoKrete-Water will yield approximately 0.45 cu. ft. | 0.013 cu. m. and will cover 5.4 sq. ft. | 0.5 sq. m. at a 1-inch | 25.4 mm thickness.

CURING

Cure in accordance with manufacturer's recommendations.

PRECAUTIONS

Avoid eye contact or prolonged contact with skin. Wash thoroughly after use. Persons using Quadex GeoKrete-Water should wear necessary PPE consisting at minimum of eye protection, dust mask and rubber gloves. Read all product labels and technical literature prior to use.