

Quad-Flow

TYPICAL PERFORMANCE CHARACTERISTICS*

- **Compressive Strength (ASTM C39)**
24-hours >5,000 psi | 34.47 MPa
28-days >12,000 psi | 82.74 MPa
- **Flexural Strength (ASTM C78)**
28-days >1,200 psi | 8.27 MPa
- **Bond Strength (ASTM C882)**
28-days >1,300 psi | 8.96 MPa
- **Modulus of Elasticity (ASTM C469)**
28-days = 5.31×10^6 psi | 36,611 MPa
- **Split Tensile Strength (ASTM C496)**
28-days >700 psi | 4.83 MPa
- **Freeze Thaw (ASTM C666)**
No visible damage after 300 cycles

* The values stated in inch-pound units are to be regarded as the standard. The values given in International System are for information only.

Invert Rehabilitation Mortar

DESCRIPTION

Quad-Flow is designed to provide high strength, quick setting invert rehabilitation mortar to work in unison with the Quadex family of repair products to form an abrasion-resistant repair while increasing the structural integrity of deteriorated pipe and culvert inverts. Quad-Flow has been developed to provide a flowable repair material, capable of being pumped into a host pipe to fill voids and repair damaged inverts with a quick setting, high strength mortar, reforming and reshaping damaged or missing inverts. The quick setting characteristics of the material allow crews to continue their work rehabilitating the host infrastructure mere hours after introduction of Quad-Flow.

RECOMMENDED FOR

Restoring storm and sanitary sewer culvert inverts:

- As stand along repair method
- A part of repair prior to applying a Quadex lining solution

FEATURES AND BENEFITS

- Quality controlled, one-component blend for uniform results.
- High strength, abrasion and corrosion resistant material.
- Fast initial set times allowing further repair activities to follow immediately behind invert rehabilitation.
- Economically available in 1,000 lb. | 453.59 kg. bulk bags.



WARRANTY

Quadex, LLC warrants its products to be free of defects in material and workmanship. Unless superseded by project specifications and terms agreed upon in writing between installer and Quadex prior to bid, if within one year from purchase, any Quadex, LLC product is proven defective, the company will replace said product or refund its purchase price at its sole discretion. The company’s obligation shall be limited solely to such replacement or refund. There are no other warranties by Quadex, LLC, expressed or implied. There is no warranty if Quadex products are used contrary to Quadex, LLC’s written directions.

PROCEDURE

Prepare void to be filled by removing unsound concrete, dirt, dust, oil and other debris using high pressure (3,500 psi | 241.3 bar) water blasting and manual/mechanical removal.

CURING

Cure in accordance with manufacturer’s recommendations.

PRECAUTIONS

Avoid eye contact or prolonged contact with skin. Wash thoroughly after use. Persons using Quad-Flow should wear necessary eye protection, dusk mask and rubber gloves. Read all product labels and technical literature.

PACKAGING/YIELD

North America

			1.0-INCH 25.4MM THICKNESS		
BAG SIZES LBS KG	BAG MATERIAL	YIELD PER BAG FT ³ M ³	BAG COVERAGE FT ² M ²	MASS COVERAGE LBS/FT ² KG/M ²	WATER PER BAG* % BY WEIGHT
1000 453.6	Super Sack	9.82 0.278	117.82 10.95	8.19 39.97	8.0 - 10.0

*Due to natural deviations in the constituent materials, additional water may be necessary on occasion. Applicators are trained to adjust as needed based upon field performance of the product.

